

Q.PEAK DUO-G7 315-330

ENDURING HIGH PERFORMANCE

A THE REAL PROPERTY OF THE PARTY OF THE PART





Q.ANTUM TECHNOLOGY: LOW LEVELISED COST OF ELECTRICITY

EUPD RESEARCH

TOP BRAND PV

EUROPE

2019

Higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 19.9%.

VDE

Quality Tested

www.VDEinfo.com ID. 40032587



INNOVATIVE ALL-WEATHER TECHNOLOGY

Optimal yields, whatever the weather with excellent low-light and temperature behaviour.



ENDURING HIGH PERFORMANCE

Long-term yield security with Anti LID Technology, Anti PID Technology¹, Hot-Spot Protect and Traceable Quality Tra.Q™.



EXTREME WEATHER RATING

High-tech aluminium alloy frame, certified for high snow (5400 Pa) and wind loads (4000 Pa).



A RELIABLE INVESTMENT

Inclusive 12-year product warranty and 25-year linear performance warranty².



STATE OF THE ART MODULE TECHNOLOGY

Q.ANTUM DUO combines cutting edge cell separation and innovative wiring with Q.ANTUM Technology.

 1 APT test conditions according to IEC/TS 62804-1:2015, method B (–1500 V, 168 h) 2 See data sheet on rear for further information.

THE IDEAL SOLUTION FOR:





Rooftop arrays on commercial and industrial buildings



QCELLS


VIELD SECURITY

TRACEABLE QUALITY

ANTI LID TECHN (ALT)

MECHANICAL SPECIFICATION

Format	66.3 in × 39.4 in × 1.26 in (including frame) (1685 mm × 1000 mm × 32 mm)			
Weight	41.2 lbs (18.7 kg)			
Front Cover	0.13 in (3.2 mm) thermally pre-stressed glass with anti-reflection technology			
Back Cover	Composite film			
Frame	Black anodized aluminum			
Cell	6 × 20 monocrystalline Q.ANTUM solar half cells			
Junction Box	2.09-3.98 in × 1.26-2.36 in × 0.59-0.71 in (53-101 mm × 32-60 mm × 15-18 mm), IP67, with bypass diodes			
Cable	4 mm² Solar cable; (+) ≥43.3 in (1100 mm), (−) ≥43.3 in (1100 mm)			
Connector	Stäubli MC4, Hanwha Q CELLS HQC4, Amphenol UTX, Renhe 05-6, Tongling TL-Cable01S, JMTHY JM601; IP68 or Friends PV2e; IP67			




ELECTRICAL CHARACTERISTICS

PO\	VER CLASS			315	320	325	330
MIN	IIMUM PERFORMANCE AT STANDARI	D TEST CONDITIO	NS, STC ¹ (POW	ER TOLERANCE +5 W / -0	OW)		
	Power at MPP ¹	P _{MPP}	[W]	315	320	325	330
Minimum	Short Circuit Current ¹	I _{SC}	[A]	9.99	10.04	10.10	10.15
	Open Circuit Voltage ¹	V _{oc}	[V]	39.84	40.10	40.36	40.62
	Current at MPP	I _{MPP}	[A]	9.51	9.56	9.61	9.67
	Voltage at MPP	V _{MPP}	[V]	33.14	33.47	33.81	34.14
	Efficiency1	η	[%]	≥18.7	≥19.0	≥19.3	≥19.6
MIN	IIMUM PERFORMANCE AT NORMAL	OPERATING CON	DITIONS, NMOT	*2			
	Power at MPP	P _{MPP}	[W]	235.9	239.6	243.4	247.1
nimum	Short Circuit Current	I _{sc}	[A]	8.05	8.09	8.14	8.18
	Open Circuit Voltage	V _{oc}	[V]	37.56	37.81	38.06	38.31
Ξ	Current at MPP	IMPP	[A]	7.48	7.52	7.57	7.61
-	Voltage at MPP	V	[V]	31.53	31.85	32.17	32.48


¹Measurement tolerances P_{MPP} ±3%; I_{SC}; V_{OC} ±5% at STC: 1000 W/m², 25±2°C, AM 1.5 according to IEC 60904-3 • ²800 W/m², NMOT, spectrum AM 1.5

Q CELLS PERFORMANCE WARRANTY



At least 98% of nominal power during first year. Thereafter max. 0.54% degradation per year. At least 93.1% of nominal power up to 10 years. At least 85% of nominal power up to 25 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Q CELLS sales organisation of your respective country.



Typical module performance under low irradiance conditions in comparison to STC conditions (25 $^\circ C,\,1000\,W/m^2)$

TEMPERATURE COEFFICIENTS

Temperature Coefficient of I _{sc}	α	[%/K]	+0.04	Temperature Coefficient of V_{oc}	β	[%/K]	-0.27
Temperature Coefficient of P _{MPP}	γ	[%/K]	-0.35	Normal Module Operating Temperature	NMOT	[°F]	109±5.4 (43±3°C)

PROPERTIES FOR SYSTEM DESIGN

Maximum System Voltage $V_{\mbox{\tiny SYS}}$	[V]	1000 (IEC)/1000 (UL)	Safety Class	II	
Maximum Series Fuse Rating	[A DC]	20	Fire Rating based on ANSI / UL 1703	C (IEC)/TYPE 2 (UL)	
Max. Design Load, Push / Pull ³	[lbs/ft ²]	75 (3600 Pa)/55 (2667 Pa)	Permitted Module Temperature	-40°F up to +185°F	
Max. Test Load, Push / Pull ³	[lbs/ft ²]	113 (5400 Pa)/84 (4000 Pa)	on Continuous Duty	(-40°C up to +85°C)	
³ See Installation Manual			•		

³See Installation Manual

QUALIFICATIONS AND CERTIFICATES

PACKAGING INFORMATION

UL 1703, VDE Quality Tested, CE-compliant, IEC 61215:2016, IEC 61730:2016,	Number of Modules per Pallet	32
Application Class II, U.S. Patent No. 9,893,215 (solar cells)	Number of Pallets per 53' Trailer	30
	Number of Pallets per 40' HC-Container	26
	Pallet Dimensions (L×W×H)	69.3 × 45.3 × 46.9 in (1760 × 1150 × 1190 mm)
UL 1703 (254141)	Pallet Weight	1415 lbs (642 kg)

Note: Installation instructions must be followed. See the installation and operating manual or contact our technical service department for further information on approved installation and use of this product.

Hanwha Q CELLS America Inc.

400 Spectrum Center Drive, Suite 1400, Irvine, CA 92618, USA | TEL +1 949 748 59 96 | EMAIL inquiry@us.q-cells.com | WEB www.q-cells.us